We claim:

1. A proton-conducting membrane, comprising a carbon-containing compound and inorganic acid, wherein

a phase-separated structure contains a carbon-containing phase containing at least 80% by volume of the carbon-containing compound and inorganic phase containing at least 80% by volume of the inorganic acid, the inorganic phase forming the continuous ion-conducting paths.

2. The proton-conducting membrane according to Claim 1, wherein said phase-separated structure is a sea-island structure with the carbon-containing phase as the island and inorganic phase as the sea.

3. The proton-conducting membrane according to Claim 1, wherein said phase-separated structure is composed of a carbon-containing phase and inorganic acid phase both in the form of continuous structure.

4. The proton-conducting membrane according to one of Claims 1 to 3, comprising a three-dimensionally crosslinked silicon-oxygen structure (A), carbon-containing compound (B) bound to (A) via a covalent bond, and inorganic acid (C).

5. The proton-conducting membrane according to Claim 4, wherein said carbon-containing compound (B) has a skeleton section substituted with hydrogen at a joint

with the three-dimensionally crosslinked silicon-oxygen structure (A), satisfying the following relationship:

$(\delta p^2 + \delta h^2)^{1/2} \leq 7(MPa)^{1/2}$

wherein, δp and δh are polarity and hydrogen bond components of the three-component solubility parameter.

6. The proton-conducting membrane according to Claim 5, wherein said carbon-containing compound (B) is bound to the three-dimensionally crosslinked silicon-oxygen structure (A) via 2 or more bonds.

7. The proton-conducting membrane according to Claim 6, wherein the skeleton section of said carbon-containing compound (B) is a hydrocarbon consisting of carbon and hydrogen.

8. The proton-conducting membrane according to Claim 7, wherein the skeleton section of said carbon-containing compound (B) has the structure represented by the following formula (1):



$\cdots$ (1)

wherein, "n" is an integer of 2 to 20.

9. The proton-conducting membrane according to Claim 7, wherein the skeleton section of said carbon-containing compound (B) has the structure represented by the following formula (2):



$$\cdots (2)$$

wherein, "n" is a natural number of 4 or less.

10. The proton-conducting membrane according to Claim 6, wherein the skeleton section of said carbon-containing compound (B) has the structure represented by the following formula (3):



$$\cdots (3)$$

wherein, R^1 and R^2 are each a group selected from the group consisting of CH_3, C_2H_5 and C_6H_5; and "l" is an integer of 2 to 20.

11. The proton-conducting membrane according to Claim 4, wherein said inorganic acid (C) is a heteropoly acid.

12. The proton-conducting membrane according to Claim 11, wherein said heteropoly acid is used in the form of being supported beforehand by fine particles of a metallic oxide.

13. The proton-conducting membrane according to Claim 11 ~~or 12~~, wherein said heteropoly acid is a compound selected from the group consisting of tungstophosphoric, molybdophosphoric and tungstosilicic acid.

14. The proton-conducting membrane of according to Claim 4, which contains 10 to 300 parts by weight of the inorganic acid (C) per 100 parts by weight of the three-dimensionally crosslinked silicon-oxygen structure (A) and carbon-containing compound (B) totaled.

15. A method for producing the proton-conducting membrane of one of Claims 1 to 14, comprising steps of preparing a mixture of a carbon-containing compound (D) having one or more hydrolyzable silyl groups and said inorganic acid (C), forming the above mixture into a film, and hydrolyzing/condensing the hydrolyzable silyl group contained

in the mixture formed into the film, to form said three-dimensionally crosslinked silicon-oxygen structure (A).

16. The method according to Claim 15 for producing the proton-conducting membrane, wherein the skeleton section of said carbon-containing compound having one or more hydrolyzable silyl groups (D) whose hydrolyzable silyl group(s) are substituted by hydrogen satisfies the following relationship:

$(\delta p^2 + \delta h^2)^{1/2} \leq 7(MPa)^{1/2}$

wherein, δp and δh are the polarity and hydrogen bond components of the three-component solubility parameter.

17. The method according to Claim 16 for producing the proton-conducting membrane, wherein said carbon-containing compound (D) having one or more hydrolyzable silyl groups has 2 hydrolyzable groups.

18. The method according to Claim 17 for producing the proton-conducting membrane, wherein said carbon-containing compound (D) having one or more hydrolyzable silyl groups is represented by the following formula (4):



$$\left(R^3\right)_{3-m} X_m Si - R^4 - SiX_m \left(R^3\right)_{3-m} \quad \cdots (4)$$

wherein, R^3 is a group selected from the group consisting of CH_3, C_2H_5 and C_6H_5; R^4 is a hydrocarbon compound consisting of carbon and hydrogen; X is a group selected from the group consisting of Cl, OCH_3, OC_2H_5 and OC_6H_5; and "m" is a natural number of 3 or less.

19. The method according to Claim 18 for producing the proton-conducting membrane, wherein said carbon-containing compound (D) having one or more hydrolyzable silyl groups is represented by the following formula (5):



$$\left(R^3\right)_{3-m} X_m Si - \left(CH_2\right)_n - SiX_m \left(R^3\right)_{3-m} \quad \cdots (5)$$

wherein, R^3 is a group selected from the group consisting of CH_3, C_2H_5 and C_6H_5; X is a group selected from the group consisting of Cl, OCH_3, OC_2H_5 and OC_6H_5; "m" is a natural number of 3 or less; and "n" is an integer of 2 to 20.

20. The method according to Claim 18 for producing the proton-conducting membrane, wherein said carbon-containing compound (D) having one or more hydrolyzable silyl groups is represented by the following formula (6):



wherein, R^3 is a group selected from the group consisting of CH_3, C_2H_5 and C_6H_5; X is a group selected from the group consisting of Cl, OCH_3, OC_2H_5 and OC_6H_5; "m" is a natural number of 3 or less; and "n" is a natural number of 4 or less.

21. The method according to Claim 17 for producing the proton-conducting membrane, wherein said carbon-containing compound (D) having one or more hydrolyzable silyl groups is represented by the following formula (7):



wherein, R^1, R^2 and R^3 are each a group selected from the group consisting of CH_3, C_2H_5 and C_6H_5; X is a group selected from the group consisting of Cl, OCH_3, OC_2H_5 and OC_6H_5; "m" is a natural number of 3 or less; and "l" is an integer of 2 to 20.

22. The method according to Claim 15 for producing the proton-conducting membrane, wherein said step of hydrolyzing/condensing the hydrolyzable silyl group to form said three-dimensionally crosslinked silicon-oxygen structure (A) uses water (E) to be contained in said mixture.

23. The method according to Claim 15 for producing the proton-conducting membrane, wherein said step of hydrolyzing/condensing the hydrolyzable silyl group to form said three-dimensionally crosslinked silicon-oxygen structure (A) is effected at 5 to 40°C for 2 hours or more.

24. The method according to Claim 15 for producing the proton-conducting membrane, wherein said step of hydrolyzing/condensing the hydrolyzable silyl group to form said three-dimensionally crosslinked silicon-oxygen structure (A) is followed by an aging step effected at 100 to 300°C.

25. The method according to Claim 15 for producing the proton-conducting membrane, wherein said step of hydrolyzing/condensing the hydrolyzable silyl group to form said three-dimensionally crosslinked silicon-oxygen structure (A) is followed by a step in

which a compound (F) having a hydrolysable silyl group is spread and hydrolyzed/condensed, effected at least once.

26. A fuel cell which incorporates the proton-conducting membrane according to one of Claims 1 to 14.